



# ROBFILM

## R8

VERSION: 161011  
Page:1/1

### MASKING FILM

#### DEFINITION

High density polyethylene film for masking. An electrostatic treatment allows a faster and more efficient adhesion to the surface.

During the production process of ROBFILM a corona treatment is also applied. This process manages to change the plastic structure, opening pores through a grinding process on the surface. The result of this process provides a great capacity to absorb any paint.

ROBFILM can support a higher electrostatic charge and offers better absorption of chemicals.

#### CHARACTERISTICS

<b>Composition:</b>	HDPE (high density polyethylene)
<b>Measures:</b>	4m x 150m 4m x 300m 6m x 100m
<b>Density:</b>	0,95 g/cm <sup>2</sup>
<b>Thickness:</b>	8 µm
<b>Transverse tensile Strength:</b>	28 N/mm <sup>2</sup>
<b>Vertical tensile Strength:</b>	55 N/mm <sup>2</sup>

#### STORAGE

<b>Storage temperature:</b>	20°C (+/- 10°C)
<b>Relative humidity:</b>	30 – 90 %
<b>Shelf life:</b>	12 months
<b>Avoid exposure to UV radiation</b>	

For any technical information contact with our Customer Attention Service or our Technical Department. ROBERLO SA declines any responsibility due to an incorrect use of the product.